

Material Data Sheet

Polycarbonate

Chemical Designation: Polycarbonate / Thin Sheet
 Abbreviation: PC
 Colours, Fillers: Clear

	Dry/moist Unit	Standard
Mechanical Properties		
Tensile strength at yield	62 MPa	DIN EN ISO 527
Elongation at yield	6 %	DIN EN ISO 527
Tensile strength at break	MPa	DIN EN ISO 527
Elongation at break	>70 %	DIN EN ISO 527
Modulus of elasticity after tensile test	2400 MPa	DIN EN ISO 527
Modulus of elasticity after flexural test	MPa	DIN EN ISO 178
Hardness		DIN 53 456 (Ball indentation hardness)
Impact resistance (23 °C)	No break kJ/m ²	DIN EN ISO 179 (Charpy)
Noched impact strength	kJ/m ²	DIN EN ISO 179
Creep rupture strength after 1000 h with static load	MPa	-
Time yield limit for 1% elongation after 1000 h	MPa	-
Coefficient of friction P = 5 MPa, v = 2 m/min, linear, on steel, hardened and ground	-	-
Wear P = 5 MPa, v = 2 m/min, distance = 2400m linear, on steel, hardened and ground	%	-
Thermal Properties		
Melting point	°C	DIN 53 765
Glass transition temperature	°C	DIN 53 765
Heat distortion temperature HDT, Method A	127 °C	ISO-R 75 Verfahren A (DIN 53 461)
Heat distortion temperature HDT, Method B	139 °C	ISO-R 75 Verfahren B (DIN 53 461)
Service temperature, short term	°C	-
Service temperature, long term	120 °C	-
Thermal conductivity (23 °C)	0.2 W/(K*m)	-
Specific heat (23 °C)	J/(g*K)	-

Material Data Sheet

Polycarbonate

	Dry/moist	Unit	Standard
Thermal Properties			
Coefficient of thermal expansion (23 – 55 °C, longitudinal)	6.5	10 ⁻⁵ *1/K	ISO 11359-2 (old DIN 53 752)
Electrical Properties			
Dielectric constant (10 ⁶ Hz)	3	-	DIN 53 483, IEC-250
Dielectric loss factor (10 ⁶ Hz)	-	-	DIN 53 483, IEC-250
Specific volume resistance	10 ¹⁶	Ω*cm	DIN IEC 60093
Surface resistance	10 ¹⁴	Ω	DIN IEC 60093
Dielectric strength	35	kV/mm	DIN IEC 60243-1
Resistance to tracking	-	-	DIN 53 480, VDE 0303 Part 1
Miscellaneous Properties			
Viscosity number (solution 0,005 g/ml sulphuric acid)		ml/g	DIN EN ISO 1133
Melt flow index (MFI)		g/10 min	DIN 53 735
Density	1.2	g/cm ³	ISO 1183
Moisture absorption to equilibrium (23°C/50RH)	0.15	%	DIN EN ISO 62
Water absorption at saturation	0.35	%	DIN EN ISO 62
Flammability acc. to UL standard 94			IEC 60695-11-10

The above information corresponds with our current knowledge and indicates our products and possible applications. We cannot give a legally binding guarantee of chemical resistance, of certain properties and the suitability of our products and their applications. Our products are not destined for use in medical and dental implants. Existing commercial patents must be observed. Unless otherwise stated, these values represent averages taken from injection moulding samples, dry as moulded. We reserve the right to make technical alterations.